

DESCRIPTION

BMI-2500 has been designed to extend the range of applications suitable for use with the Designer Molecules, Inc. imide extended bismaleimide oligomers to those in need of higher Tg and modulus. The material has excellent low pH hydrolytic resistance and thermal stability. As an additive it can improve rheological properties by increasing the thixotropic properties of a liquid monomer composition. This feature in turn can help to reduce resin bleed out on a variety of surfaces. It is soluble in most aromatic and aliphatic solvents such as toluene, xylene, NMP, etc. It can be processed in a resin system as a solid or dissolved in a solvent.

HIGHLIGHTS

• Toughener	• High adhesion to various substrates
• Hydrophobic	• Superior thermal stability

TYPICAL PHYSICAL AND CHEMICAL PROPERTIES

PROPERTY	METHOD	RESULT
Appearance at Room Temperature	Visual	Light yellow glassy powder
Functionality		2
Glass Transition	TMA	126°C
CTE α_1 / α_2	TMA	100 ppm/°C / 200 ppm/°C
Glass Transition	DMA	100°C
Modulus @	DMA	1 GPa
Melting Point (typical)	DSC	80°C
Weight Loss @ 300°C	TGA	< 0.5%
Decomposition Temperature	TGA	> 400°C
Dielectric Constant	IPC-TM-650 2.5.5.9	2.3 @ 1.5 GHz
Dissipation Factor	IPC-TM-650 2.5.5.9	< 0.001 @ 1.5 GHz
Continuous Operating Temperature (approximate)		< 180°C
Recommended Storage Temp		25°C or below

Data is for reference only and may vary depending on testing method used.

RECOMMENDED FORMULATION AND USE:

BMI-2500 is recommended for use as an additive to increase flexibility, hydrophobicity and thixotropy. When used as a base resin, it can produce films that are tough, flexible and demonstrate good peel strength.

CONTACT:

REQUEST A SAMPLE OR PLACE AN ORDER

Customer Support

☎ 858-348-1122

✉ support@designermoleculesinc.com

REF: DMI Part Number: BMI-2500